### **3M Tamper-Indicating Label Material** 7381•7384

| <b>Technical Data</b> |  |  |                     |   | October, 2006                               |  |  |
|-----------------------|--|--|---------------------|---|---|--|--|
| Product Description   | 3M <sup>™</sup> Tamper-Indicating Label Materials are designed to provide a "void" message in the facestock when removal is attempted. |  |                     |   |   |  |  |
| Construction          | Product<br>Number  | Facestock  | Destruct<br>Pattern | Adhesive  | Liner                                       |  |  |
|                       | 3M™ Tamper-<br>Indicating Label<br>Material 7381   | 2.0 mil (50 microns)<br>Gloss White Polyester            | "VOID"              | 1.0 mil (25 microns)<br>#300 "Hi-Strength"<br>Acrylic | 3.2 mil (80 microns)<br>55# Densified Kraft |  |  |
|                       | 3M™ Tamper-<br>Indicating Label<br>Material 7384   | 2.0 mil (50 microns)<br>Gloss Bright Silver<br>Polyester | "VOID"              | 1.0 mil (25 microns)<br>#300 "Hi-Strength"<br>Acrylic | 3.2 mil (80 microns)<br>55# Densified Kraft |  |  |
| Features              | • The compact (1/2" x 1-1/4  | format of the "void" "                                   | message pe          | rmits manufacture of                                  | f small labels                              |  |  |
|                       | • Adhesive provides high bond to most surfaces.  |  |                     |   |   |  |  |
|                       | • Durable polyester facestock withstands harsh environments.   |  |                     |   |   |  |  |
|                       | • 55# densified kraft liner assures consistent die cutting.  |  |                     |   |   |  |  |
|                       | • 3M label material 7381 is UL recognized in files MH 11410 and MH 16411. See the UL and CSA listing for details.                      |  |                     |   |   |  |  |

• 3M label material 7384 is UL recognized in file MH 11410 and CSA accepted file 99316.

# Application Ideas Non-transferable labels for automotive, appliance and electronics industries. Tamper-indicating labels and seals for over-the-counter drugs and other packaging applications.

# **3M<sup>™</sup> Tamper-Indicating Label Material** 7381 • 7384

| Typical Physical<br>Properties | Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.   |   |  |         |  |  |  |  |
|--------------------------------|---|---|--|---------|--|--|--|--|
|                                | Assume all surfaces to which these label materials will be applied are contaminated – metals may be oily or dusty; plastics may be coated with mold release agents, dirt, etc. Any surface contaminant will adversely affect adhesion and the destruct message; therefore, it must be removed prior to application by wiping with a solvent. Consult the manufacturer's Material Safety Data Sheet for proper handling and storage of solvents. |   |  |         |  |  |  |  |
|                                | Adheres to the following clean surfaces:  |   |  |         |  |  |  |  |
|                                | Stainless Steel P<br>ABS P  | ainted Metal Nylon<br>olyester Glass  | arbonate   |         |  |  |  |  |
|                                | Proper Handling and Storage:  |   |  |         |  |  |  |  |
|                                | Clean Substrate:  | (rubbing alcohol) or heptar   | et the application surface with a mild solvent such as isopropyl alcohol<br>bbing alcohol) or heptane and wipe thoroughly.*<br>y the surface with a lint free cloth before the solvent evaporates from<br>a surface.   |         |  |  |  |  |
|                                | Application Pressure:   | adhesion to assure "void" i<br>substrate upon removal or<br>Higher initial bonds can be | Ifficient application pressure and dwell time is required to develop<br>hesion to assure "void" message appears both on facestock and<br>bstrate upon removal or upon attempted removal through tampering.<br>gher initial bonds can be achieved through increased application<br>essure such as firm hand or squeegee pressure. |         |  |  |  |  |
|                                | Dwell Time:   | 24 hours at room temperat   | ture or 72°F (22°C) before t   | esting. |  |  |  |  |
|                                | Liner Release: 180° peel angle  |   |  |         |  |  |  |  |
|                                | Rate of Removal   | Gram  | Gram/Inch N/100 mm   |         |  |  |  |  |
|                                | 90 inches/minute  | 25 r  | max.   | 0.96    |  |  |  |  |
|                                | Conformability:   |   |  |         |  |  |  |  |
|                                | Semi-rigid, suitable for flat or slightly curved surfaces.  |   |  |         |  |  |  |  |
|                                | *Note: When using solvents, extinguish all ignition sources, and follow the manufacturer's precautions and directions for use.  |   |  |         |  |  |  |  |
| Environmental<br>Performance   | Note: The following tests are intended as a guide to product performance. Application testing is recommended using actual substrates, expected dwell times, and actual conditioning for best determination of product suitability.  |   |  |         |  |  |  |  |
|                                | The properties defined are based on the adhesion of the label material to a stainless steel test surface.   |   |  |         |  |  |  |  |
|                                | Chemical Resistance:  | Bond is secure whe  | Bond is secure when exposed to the following:  |         |  |  |  |  |
|                                |   | Auto Oil - 72<br>Weak Alkali - 4<br>Weak Acid - 4<br>MEK - 1<br>Freon®TF - 1            | hr. at room temperature<br>2 hrs. at 120°F (49°C)<br>hrs. at room temperature<br>hrs. at room temperature<br>hr. at room temperature<br>hr. at room temperature<br>2 hrs. at room temperature  |         |  |  |  |  |
|                                | Water Resistance:   | Withstands exposure   | Withstands exposure to water at room temperature for 72 hours.   |         |  |  |  |  |
|                                | Temperature Resistan  | e: Withstands exposure  | Withstands exposure from -40°F (-40°C) to 250°F (121°C).   |         |  |  |  |  |
|                                | Humidity Resistance:  | Withstands exposure   | Withstands exposure to 90°F (32°C) and 90% RH for 168 hours.   |         |  |  |  |  |

#### **3M<sup>™</sup> Tamper-Indicating Label Material** 7381 • 7384

#### Processing

#### **Incoming Label Materials:**

Every slit roll has been tested for the presence of "void" message. The leading edge of every slit roll is tabbed with a 1-1/2" strip to simulate tampering, thereby indicating that the "void" message is functional on the leading edge of that roll.

#### **Printing:**

Caution should be exercised to avoid covering the surface of the label with opaque graphics to the extent that the "void" message is hidden, and the effectiveness of the label or seal is lessened.

#### **Die-Cutting:**

The compact "void" message permits manufacture of labels as small as 1/2" x 1-1/4" (13 mm x 32 mm).

It is recommended that the converter test for the presence of the "void" message on every roll of labels or seals as the converter processes them, to insure the product quality and consistency. This can be done by laminating a label or seal to an untreated polyester film test surface. The label or seal should be wiped down with a squeegee, allowed to dwell 10 minutes and then removed to observe the presence and functions of the "void" message on both the facestock and the substrate. It is also recommended that the converter test each lot of labels or seals on the actual application surface to assure the function of the "void" message.

#### **Dispensing:**

Care should be taken not to disturb the tamper-indicating feature by pre-destructing the "void" message when manually removing the label from the liner. Slowly remove the liner from the label at a 90° angle. It is recommended that the end user test samples for each roll of labels or seals received from the converter. This should be done by laminating a representative label or seal to the specific application surface to assure its function meets expectations. This test can be run after 10 minutes dwell. However, final judgement should be based on 72 hours dwell at room temperature prior to testing.

#### **Application:**

The tamper-indicating mechanism (i.e. the "void" message both on the facestock and on the substrate) depends upon adequate adhesion of the label to the substrate. A sufficient bond may not develop on all surfaces due to low surface energy (e.g. Teflon<sup>®</sup>), contaminated or textured surfaces. Therefore, it is important to determine the suitability of the product in the intended application by carefully pretesting. The primary function of the products is to effect a non-transferable (nonreusable) label or seal by causing the "void" message to appear on the facestock when removal from the substrate is attempted. As a result of the primary function, a "void" message is also transferred to the substrate. This message transferred to substrate can be removed by hand rubbing or by solvent wiping.

Our tamper-indicating product line is designed to indicate tampering by destructing when an attempt is made to remove the label. Since no tamper-indicating feature is 100% tamper proof, careful consideration must be taken when designing labels and seals. When the consequences of tampering could be severe, such as injury or loss of human life or significant monetary loss, these products aren't recommended as the sole means of package or product tamper indication. In these instances, additional methods in combination with the labels should be considered so that the tamper-indicating features are commensurate with the requirements of the application.

### $\mathbf{3M}^{{}^{\scriptscriptstyle{\mathrm{TM}}}}\mathbf{T}\!\mathbf{a}\mathbf{m}\mathbf{p}\mathbf{e}\mathbf{r}\mathbf{-Indicating}\ \mathbf{Label}\ \mathbf{M}\mathbf{a}\mathbf{t}\mathbf{e}\mathbf{r}\mathbf{i}\mathbf{a}\mathbf{l}$

7381 • 7384

| Storage                        | Store at room temperature conditions of 72°F (22°C) and 50% relative humidity.   |  |  |  |  |
|--------------------------------|--|--|--|--|--|
| Shelf Life                     | If stored under proper conditions, product retains its performance and properties for<br>two years from date of manufacture.   |  |  |  |  |
| Product Use                    | All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.  |  |  |  |  |
| Warranty and<br>Limited Remedy | Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price. |  |  |  |  |
| Limitation of Liability        | Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.  |  |  |  |  |
|                                | (150 900112000)  |  |  |  |  |



Industrial Business Converter Markets Industrial Adhesives and Tapes Division 1030 Lake Road Medina, OH 44256-0428 800-422-8116 • 877-722-5072 (fax) www.3M.com/converter

订购热线:020-82250840



Recycled Paper 40% pre-consumer 10% post-consumer