



Thermal Transfer Polyester Label Material

7222 / 7865 • 7323 / 7863 • 7331 / 7860

Technical Data

July, 2007

Product Description 3M™ Thermal Transfer Polyester Label Materials are durable polyester stocks that offer high abrasion and chemical resistance. These materials utilize 3M™ Adhesive 300, which has excellent quick tack and also bonds well to a variety of surfaces including LSE plastics.

Construction	Product	Facestock	Adhesive	Liner
	3M™ Thermal Transfer Polyester Label Material 7222 / 7865	.002 in. (51 micron) Matte Silver Polyester Gloss TC	#300 Acrylic 0.8 mil (20 micron)	55# Densified kraft 3.2 mil (81 micron)
	3M™ Thermal Transfer Polyester Label Material 7323 / 7863	.002 in. (51 micron) Bright Silver Polyester Gloss TC	#300 Acrylic 0.8 mil (20 micron)	55# Densified kraft 3.2 mil (81 micron)
	3M™ Thermal Transfer Polyester Label Material 7331 / 7860	.002 in. (51 micron) White Polyester Gloss TC	#300 Acrylic 0.8 mil (20 micron)	55# Densified kraft 3.2 mil (81 micron)

(Calipers are nominal values.)

- Features**
- Facestock is topcoated for thermal transfer printing. Resin ribbons are recommended for optimum durability. The topcoat also provides improved ink anchorage for traditional forms of press printing.
 - Adhesive bonds well to a wide variety of substrates including metals, high surface energy (HSE) plastics and low surface energy (LSE) plastics. It is ideal for applications requiring high initial adhesion especially to LSE plastic surfaces.
 - 55# densified kraft liner assures consistent die cutting.
 - UL recognized (File MH11410) and CSA accepted (File 99316).

- Application Ideas**
- Barcode labels and rating plates.
 - Property identification and asset labeling.
 - Warning, instruction, and service labels for durable goods.
 - Nameplates and durable goods.

3M™ Thermal Transfer Polyester Label Material

7222 / 7865 • 7323 / 7863 • 7331 / 7860

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Adhesive Coat Weight	1.08 to 1.62 g/100 in. ²	3M Method E10MFP01
Release Range	10 to 60 g/2 in.	TLMI Method, 180° removal, 300 in./min.
Service Temperature	-40°F to 300°F (-40°C to 149°C)	
Minimum Application Temperature	50°F (5°C)	
Convertability	3M™ High Strength Acrylic Adhesive 300 is designed to be compatible with a variety of print methods and end use applications. Due to the quick flowing aggressive nature of this adhesive, care should be taken when converting labels for thermal transfer applications. Please refer to the die dutting/converting section of this data page or the "Guide to Converting and Handling Label Products" technical bulletin for additional information.	

Typical Peel Adhesion Properties

Adhesion: 180° peel test procedure is ASTM D 3330.

90° peel test procedure is ASTM D 3330 modified for the angle change.

	Initial (10 Minute Dwell/RT)				Conditioned for 3 Days at Room Temperature 72°F (22°C)			
	180° Peel		90° Peel		180° Peel		90° Peel	
Surface	Oz./ln.	N/100 mm	Oz./ln.	N/100 mm	Oz./ln.	N/100 mm	Oz./ln.	N/100 mm
Stainless Steel	56	61	42	46	67	73	46	50
Polycarbonate	59	67	44	48	61	67	46	50
Polypropylene	53	58	38	42	56	61	38	42
Glass	60	66	42	46	71	78	48	52
HD Polyethylene	35	38	28	31	40	44	28	31
LD Polyethylene	32	35	25	27	42	46	34	37

	Conditioned for 3 Days at 120°F (49°C)				Conditioned for 24 hours at 90°F (32°C) at 90% Relative Humidity			
	180° Peel		90° Peel		180° Peel		90° Peel	
Surface	Oz./ln.	N/100 mm	Oz./ln.	N/100 mm	Oz./ln.	N/100 mm	Oz./ln.	N/100 mm
Stainless Steel	70	77	50	55	68	74	53	58
Polycarbonate	30	33	17	19	55	60	36	39
Polypropylene	54	59	42	46	66	72	44	48
Glass	70	77	50	55	67	73	44	48
HD Polyethylene	40	44	29	32	45	49	32	35
LD Polyethylene	9	10	10	11	36	39	30	33

3M™ Thermal Transfer Polyester Label Material

7222 / 7865 • 7323 / 7863 • 7331 / 7860

Environmental Performance

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

The properties defined are based on four hour immersions at room temperature (72°F/22°C) unless otherwise noted. Samples were applied to stainless steel panels 24 hours prior to immersion and were evaluated one hour after removal from the solution for peel adhesion. Adhesion measured at 180° peel angle (ASTM D 3330) at 12 inches/minute.

Chemical Resistance:

Chemical	Adhesion to Stainless Steel		Appearance	Edge Penetration
	Oz./in.	N/100 mm	Visual	Millimeters
Isopropyl Alcohol	60	66	No change	0.8
Detergent 1% Alconox® Cleaner	64	70	No change	0
Engine Oil (10W30) @ 250°F (121°C)	64	70	No change	1
Water for 48 hours	66	72	No change	0
pH 4	65	71	No change	0
pH 10	64	70	No change	0
409® Formula	64	70	No change	0
Toluene	33	36	No change	6.5
Acetone	47	51	No change	4.3
Brake Fluid	74	81	No change	0
Gasoline	36	39	No change	5.8
Diesel Fuel	62	68	No change	1
Mineral Spirits	54	59	No change	2.4
Hydraulic Fluid	66	72	No change	0

Temperature Resistance:

300°F (149°C) for 24 hours:

no significant visual change

-40°F (-40°C) for 10 days:

no significant visual change

Humidity Resistance:

24 hours at 100°F (38°C) and 100% relative humidity:

no significant changes in
appearance or adhesion

Accelerated Aging:

ASTM D 3611: 96 hours at 150°F (65°C) and 80% relative humidity

180° Liner Release, 90 inches/minute: 16 gm./in. width (0.62 N/100 mm)

180° Peel Adhesion from Stainless Steel, 12 inches/minute: 54 oz./in. width (59 N/100 mm)

Application Techniques

For maximum bond strength, the surface should be clean and dry. Typical cleaning solvents are heptane and isopropyl alcohol.*

For best bonding conditions, application surface should be at room temperature or higher. Low temperature surfaces, below 50°F (10°C), can cause the adhesive to become so firm that it will not develop maximum contact with the substrate. Higher initial bonds can be achieved through increased rubdown pressure.

*When using solvents, read and follow the manufacturer's precautions and directions for use.

3M™ Thermal Transfer Polyester Label Material

7222 / 7865 • 7323 / 7863 • 7331 / 7860

Printing

Facestock is topcoated for improved ink receptivity and is designed for thermal transfer printing. It is also printable by all standard roll processing methods including flexography, hot stamp, letterpress, and screen printing.

UL Recognized thermal transfer ink ribbons

Advent: 301 Black; 303 Black; 501 Black; 501 Red; 501 Blue; 501 Green

Aarmor: AXR-7; AXR-7+; AXR-600

Astromed: R5, RRT, RV, RAF Blue

CP: 5440 Red; 5640 Blue; 5940 Black

Dasco: DR-74; DR-84

Great Ribbon: SDR

ICS: ICS-CC-4099.1

Iimak: SP-330; PrimeMark

Intermec: 053258-2; 054048-4

Japan Pulp and Paper: JP Resin 1; JP Resin 2 Blue; JP Resin 2 Red (suitable for indoor use only); JP Resin 2 Green (suitable for indoor use only)

Kurz: K500; K501; K815

Markem: 716 (suitable for indoor use only)

Mid City Columbia: CGL-80; CGL-80HE

NCR: Matrix Resin; Matrix; PaceSetter; Promark II; Ultra V

Pelikan: T016

Ricoh: B110A; B110C; B110CX

Sato: Premier 1

Sony: 4070; 4072; 4075; 4085; 5070; TR6070; TR6075; Signature Series Resin; Signature Series Wax

UBI: HR03; HR04

Zebra: 5095; 5099; 5100; 5175

Die Cutting/Converting

Rotary die cutting is recommended. Fanfolding of labels is not recommended. Small labels should be evaluated carefully. Winding tensions should be kept at a minimum to help prevent the adhesive from oozing.

Packaging

Finished labels should be stored in plastic bags.

3M™ Thermal Transfer Polyester Label Material

7222 / 7865 • 7323 / 7863 • 7331 / 7860

Storage	Store at room temperature conditions of 72°F (22°C) and 50% relative humidity.
Shelf Life	If stored under proper conditions, product retains its performance and properties for two years from date of manufacture.
Product Use	All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.
Warranty and Limited Remedy	Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.
Limitation of Liability	Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001:2000

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.



Industrial Adhesives and Tapes Division Converter Markets

1030 Lake Road
Medina, OH 44256-0428
800-422-8116 • 877-722-5072 (fax)
www.3M.com/converter



Recycled Paper
40% pre-consumer
10% post-consumer

3M is a trademark of 3M Company.
Alconox is a registered trademark of
Alconox, Inc.
409 is a registered trademark of Clorox.
Printed in U.S.A.
©3M 2007 70-0709-1016-4 (7/07)